



La MISOLET

Working Of Electric And Thermo Insulating Materials

CNC machining by customers' drawing
 Blanked findings
 Direct selling
 Sheets and panels – Rods – Tubes made of:
 Bakelized Cloth and Bakelized Paper
 Epoxy Glass Nema G10 and G11,
 Silicone Nema G7 and Melamine Nema G5
 Polyester Glass GPO3
 Thermo Insulating Materials – Mica and Micanite
 TOOLING, BLANKING AND DIEMAKING

DATA SHEET

Laminate: **LTFE**

Description: Cotton fabric (36x36 ±2) and phenolic resin laminate

According to specifications	CEI 15/10	FF	Unit	Average values	Test method	Test conditions
	CEI EN 60893	PF CC 203				
	DIN 7735	Hgw 2083				
	NEMA LI - 1	L				
Physical properties	Colour			brown		
	Specific gravity		g/cm ³	1,4	ISO 1183	a
	Water absorption mm 3		mg	249	IEC 60893-2	b + d
	Thermal classification		°C	E (120°C)	IEC 60216	-
	Self extinguishing			HB	UL 94	-
	Thermal conductivity		W/mK	0,2	ISO 8302	-
	Expansion coefficient		10 ⁻⁶ /K	18	VDE 0304/VSM	-
	Silicone resin content		%	-	IEC 371-2	-
	Mica content		%	-	IEC 371-2	-
Mechanical properties	Flexural strength ⊥		MPa	158	ISO 178	a
	Charpy impact strength		KJ/m ²	11,3	ISO 179	a
	Tensile strength		MPa	102	ISO 527	a
	Compressive strength ⊥		MPa	342	ISO 604	a
	Bonding strength //		N	7000	CEI	a
	Modulus of elasticity		MPa	7000	ISO 178	a
Dielectrical properties	Insulation resistance		MΩ	1	ISO 60167	d
	Dielectric strength // to lamination		KV	2	ISO 60243-1	a
	Dielectric strength ⊥ to lamination		KV/mm	0,6	ISO 60243-1	a
	Tracking resi stance		V	-	IEC 60112	-
	Arc resistance		S	-	ASTM D495	-
	Dissipation factor at 1 MHz			-	IEC 60250	-
	Dielectric constant (permittivity) at 1 MHz			-	IEC 60250	-

The values shown above are indicative as they represent the average values observed during our routine control tests.

The user must make sure that the product he requests is compatible with the use to which it is destined.

Test condition:

- a) 48h 15-35°C 45/75 % relative humidity
- b) 1h 105°C
- c) 24h 105°C
- d) 24h 23°C in water
- e) 48h 50°C in water
- f) 24h 120°C in oil
- g) 96h 45°C 95% relative humidity

(Page 1 of 2)

Laminate: **LTFE**

La MISOLET



THICKNESS mm	TOLERANCE	Particular properties:
0,5	± 0,13	- Suitable for punching - Used for fine machining applications
0,6	± 0,14	
0,8	± 0,15	
1,0	± 0,16	
1,2	± 0,17	
1,5	± 0,19	
2,0	± 0,21	
2,5	± 0,24	
3,0	± 0,26	
3,5	± 0,28	
4,0	± 0,32	
5,0	± 0,36	
6,0	± 0,40	
8,0	± 0,49	
10,0	± 0,56	
12,0	± 0,64	
14,0	± 0,70	
16,0	± 0,76	
18,0	± 0,81	
20,0	± 0,87	
25,0	± 1,02	
-	-	
-	-	
-	-	
-	-	
-	-	

TO BE KEPT in dry stores, in a horizontal position

CAUTION: this material is photosensitive, light can gradually change the shade of colour.

We are available to effect cutting to measurement as well as machining to drawing of parts by CNC

Ref.217.798-100218; 216.8623-150706;

Ed. October 2019