

CNC machining by customers' drawing
Blanked findings
Direct selling
Sheets and panels – Rods – Tubes made of:
Bakelized Cloth and Bakelized Paper
Epoxy Glass Nema G10 and G11,
Silicone Nema G7 and Melamine Nema G5
Polyester Glass GPO3
Thermo Insulating Materials – Mica, Micanite
TOOLING, BLANKING AND DIEMAKING

## **DATA SHEET**

Laminate:

**LBNN** 

**Description:** Paper base laminate with phenolic resin binder suitable for hot

punching up to and including 3 mm

According to specifications

Colour

**Physical** 

 CEI 15/10
 TR

 CEI EN 60893
 PF CP 207

 DIN 7735
 Hp 2061

 NEMA LI - 1
 XP

Unit Average Test Test values method s

black

,	00.00.		2.0.0.1	the state of the s	
properties	Specific gravity	g/cm³	1,4	ISO 1183	а
	Water absorption mm 1	mg	200	IEC 60893-2	b + d
	Thermal classification	°C	E (120°C)	IEC 60216	-
	Self extinguishing		НВ	UL 94	-
	Thermal conductivity	W/mK	0,25	ISO 8302	-
	Expansion coefficient	10 <sup>-6</sup> /K	-	VDE 0304/VSM	-
	Silicone resin content	%	-	IEC 371-2	-
	Mica content	%	-	IEC 371-2	-
Mechanical	Flexural strength $ot$	MPa	140	ISO 178	а
properties	Charpy impact strength	KJ/m²	-	ISO 179	-
	Tensile strength	MPa	130	ISO 527	-
	Compressive strength ⊥	MPa	-	ISO 604	-
	Bonding strength //	N		CEI	-
	Modulus of elasticity	MPa	-	ISO 178	-
Dielectrical	Insulation resistance	МΩ	-	ISO 60167	-
properties	Breakdown voltage	KV	30	ISO 60243-1	а
	Dielectric stength ⊥ to lamination	KV/mm	1	ISO 60243-1	-
	Tracking resi stance	V	-	IEC 60112	-
	Arc resistance	S	-	ASTM D495	-
	Dissipation factor at 1 MHz		-	IEC 60250	-
	Dielectric constant (permittivity) at 1 MHz		-	IEC 60250	-

We inform you that the data reported on the data sheet are provided to the end user for the sole purpose of providing a range of parameters in order to assess the hypothetical suitability of the product to the actual use of the same, therefore to be considered indicative as they represent average values from laboratory tests. The user must then test the product to determine its properties and its suitability for its intended use.

Misolet s.r.l expressly disclaims all liability for any damage, injury and costs to persons and/or property, arising directly or indirectly from the use of the product that has not been preceded by tests with respect to the conditions of use to which the same will be intended. The data contained in this data sheet does not constitute a guarantee of any kind, express or implied, including any suitability for a particular use or purpose.

## **Test condition:**

a) 48h 15-35°C 45/75 % relative humidity b) 1h 105°C c) 24h 105°C d) 24h 23°C in water

e) 48h 50°C in water f) 24h 120°C in oil g) 96h 45°C 95% relative humidity

(Page 1 of 2)

Sede Legale: Via Verbano, 8 - 20139 Milano



CNC machining by customers' drawing
Blanked findings
Direct selling
Sheets and panels – Rods – Tubes made of:
Bakelized Cloth and Bakelized Paper
Epoxy Glass Nema G10 and G11,
Silicone Nema G7 and Melamine Nema G5
Polyester Glass GPO3
Thermo Insulating Materials – Mica, Micanite
TOOLING, BLANKING AND DIEMAKING

Laminate: LBNN

THICKNESS mm	TOLERANCE	Particular properties:	
0,3	± 0,06	- Good dielectric characteristics	
0,4	± 0,07	- Fair mechanical properties	
0,5	± 0,08	- Suitable for punching	
0,6	± 0,09		
0,8	± 0,10		
1,0	± 0,12		
1,2	± 0,14		
1,5	± 0,15		
2,0	± 0,19	Application advice:	
2,5	± 0,22	- It is used in low voltage equipment	
3,0	± 0,25	- Panels	
- 4	- /	- Supports	
-	- /		
-	-		
-	/-		
-	/ -		
-	-		

TO BE KEPT in dry stores, in a horizontal position We are available to effect cutting to measurement as well as machining to drawing of parts by CNC

Rif.217.798-010720; 251021; 216.230-4-200326; 216.8623-a1-161021;

Edit. January 2022 (Page 2 of 2)